
[Material Data Sheet]

D2 Corrosion Resistant Tool Steel



COMPOSITION %			
Balance			
11.00 - 13.00			
1.40 - 1.60			
0.70 - 1.20			
0.00 - 1.10			
0.00 - 0.60			
0.00 - 0.60			
0.00 - 0.30			
0.00 - 0.25			
0.00 - 0.03			
0.00 - 0.03			

MECHANICAL	PROPERTIES

Standard	Studio System 2 ² After quench and temper	
ASTM B528	3.1	
ASTM E18	56.5	
g/cm³	7.53	
s coupled with c	orrosion resistance	
s		
Tool components for press & sintering powder metallurgy (punches & dies)		
	ASTM B528 ASTM E18 g/cm ³ s coupled with c nt	

OTHER STANDARD DESIGNATIONS ¹

UNS T30402

AMTS A681

DIN 1.2379

1. Listed designations are for reference purposes only. Composition and mechanical properties may vary.

2. Heat treated samples were solutionized at 1025 °C for 30 minutes, air cooled, and then double tempered at 450 °C for 1 hour per temper.

End-use material performance is impacted (+/-) by certain factors including but not limited to part geometry and design, application and evaluation conditions, etc. Hardness, TRS and density data reported are mean values minus 1 sigma.